

# Indonesian Teak—Wire Brushed



**Pioneer millworks**  
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



We've searched the globe to bring you environmentally friendly and ethically sourced teak. This extremely versatile species is reclaimed from non-Burmese sources and is socially responsible—currently, 1% of our teak sales are donated to the Borneo Project in their fight to end the loss of habitat for the indigenous peoples of Indonesia.

Our Wire Brushed grade has a lightly textured surface that gives depth to the swirling tans and toffee browns of the wood. Tight grain makes Teak strong and durable, able to withstand the wear and tear of shoes, animals, and weather. Natural oils make it resistant to rot, insects, and fungi. Thanks to its water resistant nature, consider including the warm tones and texture of Teak in place of tile in places like kitchens and baths. Add a color finish to customize your hue, use it indoors or outdoors, on vertical or horizontal surfaces—the versatility of teak makes it a valuable arsenal in any design tool-kit.



# Pioneer Millworks Indonesian Teak—Wire Brushed

4/2018

## CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring

06 42 00—Wood Paneling

## MANUFACTURER

Pioneer Millworks  
1180 Commercial Drive  
Farmington, NY 14425  
Phone: 800-951-9663

Pioneer Millworks  
2609 SE 6th Avenue  
Portland, OR 97202  
Phone: 503-719-4800

## MATERIALS

1. **Product Name:** Indonesian Teak Wire Brushed
2. **Species/Description:** Indonesian Teak, smooth planed and wire-brushed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from golden tan to toffee brown.  
Unlimited color variation is inherent to the product.
5. **Grade:** Wire Brushed
6. **Dimensions:**
  - Solid**  
TH—3/4"  
WD—4 7/8"– 8 5/8" as specified  
LG—24" to 108" random
  - Engineered**  
TH—9/16"  
WD—3 1/8" to 8 5/8" as specified  
LG—24" to 108" random
7. **Milling:** Tongue and Groove Micro Bevel Edge (TGMBVE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 1070  
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** None

## ADDITIONAL INFORMATION

**Heartwood:** No restriction

**Grain:** No restriction

**Knots:** No limitations on sound knots, surface defects from chipped or open knots may be present.

**Texture:** Surface should be 95% clear of saw marks or patina.  
Material is wire-brushed to open up the grain.

**Voids:** Nail, bolt and other mechanical holes can be present and occasionally reach 3/8" in diameter. Voids up to 2" in diameter may be filled with oval plugs.

**Discoloration:** Ferrous staining from previous fasteners may be present.

**Checks:** Structural checks not affecting the integrity of the plank, once installed, are allowed.

**Moisture Content:** Kiln dried 6–9% prior to milling.

## LEED INFORMATION

MRc3: Materials Reuse

(materials used for this credit cannot be applied to MRc4 or MRc5)

MRc4: Recycled Content, 100% Post-Consumer Recycled Content  
(materials used for this credit cannot be applied to MRc3 or MRc7)

## RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.