

American Prairie—Faux Painted



Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Our take on barn wood paneling is broad and dynamic in scope. We incorporate wood that is salvaged not just from barns but also from agricultural fencing and other structures that have endured the elements. Our Faux Painted American Prairie allows you to choose the accent colors and our finishing experts will create a finished look that is authentic as its original painted cousin.



Pioneer Millworks American Prairie—Faux Painted

2/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

- Product Name:** American Prairie Faux Painted
- Species/Description:** Domestic Mixed Hardwoods and/or Softwoods with original patina.
- Source:** Agricultural/Industrial deconstruction
- Color:** Tones may range from brown to grey with applied red or white paint. Unlimited color variation is inherent to the product.
- Grade:** Faux Painted
- Dimensions:**
 - Solid**
TH—5/8" to 1" variable
WD—4" to 10" as specified
LG—24" to 144" random
 - Engineered**
TH—N.A.
WD—N.A.
LG—N.A.
- Milling:** Ripped on two edges (R2E)
- Finish:** Unfinished unless specified otherwise
- Hardness:** 420–1100
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
- FSC Claim:** (SCS-COC-003998)
Solid: Recycled 100%
Engineered: N.A.

ADDITIONAL INFORMATION

- Heartwood:** No restriction
Grain: No restriction
Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.
Texture: This mixture shows a varied pattern of saw marks, wear patterns, colors and textures. Overwood of up to 1/8" can be expected.
Voids: Nail, bolt and other mechanical holes can be present and occasionally reach 2" in diameter. Surface defects from insect marks, including pin holes may be present.
Discoloration: Ferrous staining from previous fasteners may be present
Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.
Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

- MRc3: Materials Reuse
(materials used for this credit cannot be applied to MRc4 or MRc5)
MRc4: Recycled Content, 100% Post-Consumer Recycled Content
(materials used for this credit cannot be applied to MRc3 or MRc7)
MRc5: Regional Materials (call for details)
MRc7: Solid Materials are FSC Recycled 100%

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Shown in white and red—many color options available.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.