

Black & Tan—Tan Mixed Oak



This reclaimed mix of Red and White Oak features hints of its original non-toxic black paint from its previous life as horse farm fencing deep in the grain and fissures of the smooth planed surface. An exciting blend of warm tones with varying lights and darks, you'll find occasional knots and a modest price point on these single width reclaimed planks.



Pioneer Millworks

Black & Tan—Tan Mixed Oak

2/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Black & Tan—Tan
2. **Species/Description:** Domestic Red and White Oak, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from tan to pink
Unlimited color variation is inherent to the product
5. **Grade:** Tan
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—4" to 5" as specified
LG—18" to 96" random
 - Engineered**
TH—5/8"
WD—4" to 5" as specified
LG—12" to 96" random
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 1290
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid: Recycled 100%
 - Engineered: FSC Mix 70%.

ADDITIONAL INFORMATION

- Heartwood:** No restriction
Grain: No restriction
Knots: No limitations on sound knots, surface defects from chipped or open knots may be present
Texture: Surface should be 95% clear of saw marks or patina
Voids: Nail, bolt and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect marks, including pin holes may be present. Peg or bolt holes are often left open in longer planks
Discoloration: Ferrous staining from previous fasteners may be present
Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases
Moisture Content: Kiln dried 6–9% prior to milling

LEED INFORMATION

- MRc3: Materials Reuse
(materials used for this credit cannot be applied to MRc4 or MRc5)
MRc4: Recycled Content, 100% Post-Consumer Recycled Content
(materials used for this credit cannot be applied to MRc3 or MRc7)
MRc5: Regional Materials (call for details)
MRc7: Solid Materials are FSC Recycled 100%

RECOMMENDED OVERAGE

Recommend 7-12% additional material for on-site grading, trimming and installation factors



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.