

# Karri—Bright



**Pioneer millworks**  
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Salvaged from educational buildings in Australia, our reclaimed Karri has the look of rainforest grown Mahogany without the environmental impact. When we mill Karri—it reveals a deep range of reds and browns, with a tight grain and occasional pitch pockets and nail holes, this reclaimed wood is among the hardest we offer making it a great choice for high traffic floors. (We think walls wear it well too.)



# Pioneer Millworks Karri—Bright

2/2018

## CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring  
06 42 00—Wood Paneling

## MANUFACTURER

Pioneer Millworks  
1180 Commercial Drive  
Farmington, NY 14425  
Phone: 800-951-9663

Pioneer Millworks  
2609 SE 6th Avenue  
Portland, OR 97202  
Phone: 503-719-4800

## MATERIALS

1. **Product Name:** Karri Bright
2. **Species/Description:** Australian Karri, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from red to brown. Unlimited color variation is inherent to the product.
5. **Grade:** Bright
6. **Dimensions:**
  - Solid**  
TH—1/2" or 5/8" as specified  
WD—4" nominal  
LG—18" to 144" random
  - Engineered**  
TH—5/8"  
WD—4" nominal  
LG—12" to 96" random
7. **Milling:** Tongue and Groove Square Edge (TGSQE) or Surfaced on four faces (S4S)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 2000  
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
  - Solid: Recycled 100%
  - Engineered: FSC Mix 70%

## ADDITIONAL INFORMATION

- Heartwood:** No restriction  
**Grain:** No restriction  
**Knots:** No limitations on sound knots, surface defects from chipped or open knots may be present.  
**Texture:** Surface should be 95% clear of saw marks or patina.  
**Voids:** Nail, bolt and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect marks, including pin holes may be present. Peg or bolt holes are often left open in longer planks  
**Discoloration:** Ferrous staining from previous fasteners may be present.  
**Checks:** Structural checks not affecting the integrity of the plank, once installed, are allowed. Very limited gum veins.  
**Moisture Content:** Kiln dried 6–9% prior to milling.

## LEED INFORMATION

- MRC3: Materials Reuse  
(materials used for this credit cannot be applied to MRC4 or MRC5)  
MRC4: Recycled Content, 100% Post-Consumer Recycled Content  
(materials used for this credit cannot be applied to MRC3 or MRC7)  
MRC5: Regional Materials (call for details)  
MRC7: Solid Materials are FSC Recycled 100%; Engineered FSC Mix 70%

## RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.