


Shou Sugi Ban—Color Char

Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Shou Sugi Ban is an ancient Japanese technique of burning wood as a preservative treatment for exterior siding. Color Char is most often applied to our sustainably harvested Larch, though we're open to other species. This grade is lightly toasted, brushed back to highlight the grain, and then highlighted with color. Hues and mixes are up to you, but we do have some tried suggestion that we're highlighting here. Chat with our local wood designers about your ideas and to get some samples.

Used most often as paneling for both interior and siding for exterior use, the char and color level can change over time, depending on its exposure to the elements. We treat our Shou Sugi Ban Color Char with a clear exterior oil to help slow wear. The evolving look suggests the Japanese aesthetic of wabi-sabi—a reminder of the transience and imperfection of all things.



Pioneer Millworks

Shou Sugi Ban—Color Char

8/20/18

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Shou Sugi Ban—Color Char
2. **Species/Description:** Domestic Larch, circle sawn or smooth planed
3. **Source:** Sustainably Harvested Forests
4. **Color:** Tones will range from toasted tan to charcoal black with custom color tints
5. **Grade:** Select and Better
6. **Dimensions:**
 - Solid**
TH— 3/4"
WD— 6" nominal
LG— 18" to 144" random
 - Engineered**
TH—N.A.
WD—N.A.
LG—N.A.
7. **Milling:** Ripped two edges (R2E) or Shiplap no reveal
8. **Finish:** Burned and finished with a tinted exterior oil
9. **Hardness:** 830
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** None

ADDITIONAL INFORMATION


Heartwood: No restriction.
Grain: No restriction.
Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.
Texture: Surface may have a circle sawn or deeply wire-brushed texture.
Voids: Occasional blown out knots up to 1" diameter may be present.
Discoloration: The intensity of burn may vary across the length of each board.
Checks: No restriction.
Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: N.A.
MRc4: N.A.
MRc5: Regional Materials (call for details)
MRc7: N.A.

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.