

Mixed Softwoods—Vat Stock Patina

Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Sourced from the food or wine industries, this mix of tightly grained softwoods made the vats that held fruits, pickles, wine, water, and vinegar. Both sides of these planks offer a range of deep browns, silvery greys, and occasional rusts, with evidence of the hardware embossed into the surface, and staining from the contents deep into the grain.



Pioneer Millworks Mixed Softwoods—Vat Stock Patina

2/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Vat Stock Patina
2. **Species/Description:** Domestic Mixed Softwoods with Original Patina
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range widely from brown to grey to black with occasional perpendicular strap marks. Unlimited color variation is inherent to the product.
5. **Grade:** Patina
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—5" nominal
LG—18" to 108" random
 - Engineered**
TH—N.A
WD—N.A
LG—N.A.
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 660
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid: Recycled 100%
 - Engineered: N.A.

ADDITIONAL INFORMATION

Heartwood: No restriction
Grain: No restriction
Knots: Typically clear with few knots.
Texture: No restriction
Voids: Very infrequent nail holes.
Discoloration: Ferrous staining from previous fasteners may be present.
Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.
Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse
(materials used for this credit cannot be applied to MRc4 or MRc5)
MRc4: Recycled Content, 100% Post-Consumer Recycled Content
(materials used for this credit cannot be applied to MRc3 or MRc7)
MRc5: Regional Materials (call for details)
MRc7: Solid Materials are FSC Recycled 100%

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.