



photo for representation only

## American Gothic **Reclaimed Ash**

### **Density**

No limit on grain density

### **Hardness**

1320

### **Heartwood**

No limit on combination of heartwood and sapwood

### **Grain**

A mixture of flat sawn and vertical grain

### **Color**

No restriction on natural color variation

### **Knots**

No limitation on sound knots. Surface defects resulting from chipped or broken knots will be present

### **Texture**

Re-sawing and milling removes all but infrequent saw marks and previous wear patterns. Very occasional overwood from natural variation in surface is possible.

### **Holes**

Nail and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect tracks and pin holes will be present at times in heavy concentrations.

### **Discoloration**

Ferrous staining from previous fasteners may be present.

### **Checks**

Checks and crack allowed to 3/32" in widths less than 7". In widths 7" and wider these sizes increase.

### **Moisture Content**

Kiln dried to 6 – 9% unless otherwise requested

### **Finish**

Standard product is supplied unfinished

## **Certifications**

### **FSC**

FSC Recycled 100% credit

### **LEED**

MR 4.1 & 4.2 (Material Reuse)

MR 5.1 & 5.2 (Materials)

\* Grading applies to flooring and boardstock, all material graded best face.