



photo for representation only

Knotty'N'Naily **Reclaimed Douglas Fir**

Density

No restriction on grain density

Hardness

660

Heartwood

Unlimited combination of heartwood and sapwood

Grain

No restriction on grain orientation

Color

Unlimited color variation

Knots

Unlimited sound, tight knots permitted, some surface defects from chipped/open knots

Texture

Re-sawing and milling removes all but very infrequent saw marks and previous wear patterns

Holes

Unlimited nail holes, occasional bolt holes, peg holes, and open knots

Discoloration

May have blue stain in sapwood; ferrous stain allowed throughout

Checks

Checks not affecting structural integrity allowed. No discernible shake. Sound pith allowed.

Moisture Content

Kiln dried to 6 – 9% unless otherwise requested

Finish

Standard product is supplied unfinished

Certifications

FSC

FSC Recycled 100% credit

LEED

MR 4.1 & 4.2 (Material Reuse)

MR 5.1 & 5.2 (Materials)

* Grading applies to flooring and boardstock, all material graded best face.