



photo for representation only

American Gothic **Reclaimed Hickory**

Density

No limit on grain density

Hardness

1820

Heartwood

No limit on combination of heartwood and sapwood

Grain

A mixture of flat sawn and vertical grain

Color

Highly variable, with no restriction

Knots

No limitation on sound knots. Surface defects resulting from chipped or broken knots will be present

Texture

Re-sawing and milling removes all but infrequent saw marks and previous wear patterns. Very occasional overwood from natural variation in surface is possible.

Holes

Nail and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect tracks and pin holes will be present at times in heavy concentrations.

Discoloration

Ferrous staining from previous fasteners may be present.

Checks

Checks and crack allowed to 3/32" in widths less than 7". In widths 7" and wider these sizes increase.

Moisture Content

Kiln dried to 6 – 9% unless otherwise requested

Finish

Standard product is supplied unfinished

Certifications



The mark of responsible forestry

FSC

FSC Recycled 100% credit
Pioneer Millworks Chain of Custody #: SCS-COC-003998

LEED

MR 4.1 & 4.2 (Material Reuse)
MR 5.1 & 5.2 (Materials)

* Grading applies to flooring and boardstock, all material graded best face.