



photo for representation only

## Character Select **Antique Heart Pine**

### Density

50% dense grain, 8 rings or more per inch

### Hardness

1225

### Heartwood

75% Heartwood

### Grain

No restriction on mixture of flat sawn and vertical grain

### Color

Unlimited color variation

### Knots

Sound knots allowed, occasional black knots. No limitations on frequency of sound knots. Max size shall be approx. 2" diameter in boards less than 6" wide, 3" diameter in boards 6" and wider

### Texture

Re-sawing and milling removes all but very infrequent saw marks and previous wear patterns

### Holes

Nail holes generally limited to 1/4" diameter. Up to 20% boards can be naily. Occasional bolt holes and edge nail holes.

### Discoloration

Unlimited ferrous staining usually found around fastener holes, blue stain may be present in sapwood

### Checks

Non-structural checks occasionally allowed up to 1/8" wide. Sound pith allowed.

### Moisture Content

Kiln dried to 6 – 9% unless otherwise requested

### Finish

Standard product is supplied unfinished

## Certifications



The mark of responsible forestry

### FSC

FSC Recycled 100% credit  
Pioneer Millworks Chain of Custody #: SCS-COC-003998

### LEED

MR 4.1 & 4.2 (Material Reuse)  
MR 5.1 & 5.2 (Materials)

\* Grading applies to flooring and boardstock, all material graded best face.

1180 Commercial Dr, Farmington, NY 14425 | 2675 NE Orchard Ave, McMinnville, OR 97128 | 800.951.WOOD | [pioneermillworks.com](http://pioneermillworks.com)