



photo for representation only

Foundry **Maple**

Density

No limit on grain density

Hardness

1450

Heartwood

No limit on combination of heartwood and sapwood

Grain

A mixture of grain orientations

Color

No restriction on color variation. Original distressing, surface staining, and paint may be present.

Knots

No limit on sound knots. Surface defects resulting from chipped or broken knots will be present

Texture

Texture variation from original surface finish, wear, and environmental conditions

Holes

Nail and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect tracks and pin holes will be present at times in heavy concentrations.

Discoloration

Ferrous staining from previous fasteners and rough distressing may be present

Checks

Checks and cracks allowed to 3/32" in widths less than 7".

Moisture Content

Kiln dried to 6 – 9% unless otherwise requested

Finish

Standard product is supplied with no new finish applied, original finish may be present

Lengths

T&G: 12"–12' Random, Square Edge: 6"–16' Random

*May include original end-matching depending on the batch. A small percentage of material may include square ends resulting from defecting.

Certifications



The mark of responsible forestry

FSC

FSC Recycled 100% credit
Pioneer Millworks Chain of Custody #: SCS-COC-003998

LEED

MR 4.1 & 4.2 (Material Reuse)
MR 5.1 & 5.2 (Materials)

* Grading applies to flooring and boardstock, all material graded best face. REV#PMW09112014