

Indonesian Teak—Ready-made Panels

Pioneer Millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



We've searched the globe to bring you environmentally friendly and ethically sourced teak. This extremely versatile species is reclaimed from non-Burmese sources and is socially responsible—currently, 1%

of our teak sales are donated to the Borneo Project in their fight to end the loss of habitat for the indigenous peoples of Indonesia.

Our ready-made panels celebrate the unmatched character of the 18th and 19th century plank, and are customizable (shown here in a Versailles pattern). Tight grain makes Teak strong and durable, able to withstand the wear and tear of shoes and animals. Natural oils make it resistant to rot, insects, and fungi.



Pioneer Millworks Indonesian Teak—Ready-made Panels

10/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring

06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Teak Read-made Panels
2. **Species/Description:** Indonesian Teak, smooth planed or with original patina as specified. Assembled in various patterns
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from golden tan to chocolate brown. Unlimited color variation is inherent to the product.
5. **Grade:** Ready-made Panels
6. **Dimensions:**
 - Solid**
 - TH—N.A.
 - WD—N.A.
 - LG—N.A.
 - Engineered As Shown**
 - TH—3/4" as specified
 - WD—34.25"
 - LG—34.25"
 - (Custom sizes are available)
7. **Milling:** Square Edge (SQE) or T&G with Microbevel
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 1070
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** None

ADDITIONAL INFORMATION

Heartwood: No restriction.

Grain: No restriction.

Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.

Texture: This mixture may show a varied pattern of saw marks, wear patterns, colors and texture, or be smooth planed as specified. Overwood of up to 1/8" can be expected.

Voids: Nail, bolt and other mechanical holes can be present and occasionally reach 3/8" in diameter. Voids up to 2" in diameter may be filled with oval plugs.

Discoloration: Ferrrous staining from previous fasteners may be present. Some original paint remnants may be present.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed.

Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse (materials used for this credit cannot be applied to MRc4 or MRc5)

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Shown in a Versailles pattern—panels are customizable.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.