

Karri—Bright



Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Salvaged from educational buildings in Australia, our reclaimed Karri has the look of rainforest grown Mahogany without the environmental impact. When we mill Karri—it reveals a deep range of reds and browns, with a tight grain and occasional pitch pockets and nail holes, this reclaimed wood is among the hardest we offer making it a great choice for high traffic floors. (We think walls wear it well too.)



Pioneer Millworks

Karri—Bright

12/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring

06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Karri Bright
2. **Species/Description:** Australian Karri, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from red to brown. Unlimited color variation is inherent to the product.
5. **Grade:** Bright
6. **Dimensions:**
 - Solid**
TH—1/2" or 5/8" as specified
WD—4" nominal
LG—18" to 144" random
 - Engineered**
TH—5/8"
WD—4" nominal
LG—12" to 96" random
7. **Milling:** Tongue and Groove Square Edge (TGSQE) or Surfaced on four faces (S4S)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 2000
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid:** FSC Recycled 100%
 - Engineered:** FSC Mix

ADDITIONAL INFORMATION

Heartwood: No restriction

Grain: No restriction

Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.

Texture: Surface should generally be 95% clear of saw marks or patina.

Voids: Fastener holes can be present and occasionally reach 3/8" in diameter.

Surface defects from insect marks, including pin holes may be present.

Voids caused by open gum pockets may be present in some boards.

Discoloration: Ferrous staining from previous fasteners may be present.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed. Very limited gum veins.

Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse

(materials used for this credit cannot be applied to MRc4 or MRc5)

MRc4: Recycled Content, 100% Post-Consumer Recycled Content

(materials used for this credit cannot be applied to MRc3 or MRc7)

MRc5: Regional Materials (call for details)

MRc7: Solid Materials are FSC Recycled 100%; Engineered FSC Mix

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change.
All photos for representation only. Additional information
available at our website or call our wood design experts.