

Mixed Hardwoods—Settlers' Plank



Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



A mosaic of hardwood species native to the Northeastern US, you'll find things like Ash, Elm, Hickory, Beech, Oak, and Maple mixed in, all skip planed to maximize their rugged patina and saw marks. On a floor, this begs for heavy traffic, hiding even the heaviest wear in its mix of colors and textures. Ranging from deepest black-brown to light tan, every plank speaks to the previous life of this mix of reclaimed woods—perfect for accent walls or flooring.



Pioneer Millworks Mixed Hardwoods—Settlers' Plank

12/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Settlers' Plank Mixed Hardwoods
2. **Species/Description:** Domestic Hardwoods with original patina
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from gold to brown to grey.
Unlimited color variation is inherent to the product.
5. **Grade:** Settlers' Plank
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—3" to 10" as specified
LG—18" to 144" random
 - Engineered**
TH—5/8"
WD—4" to 8" as specified
LG—12" to 96" random
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 770–1450
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid:** FSC Recycled 100%
 - Engineered:** FSC Mix

ADDITIONAL INFORMATION

Heartwood: No restriction

Grain: No restriction

Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.

Texture: This mixture shows a varied pattern of saw marks, wear patterns, colors and textures. Material is surfaced so that approximately 50% of the original patina remains. Generally, 70% of boards have some patina. Overwood of up to 1/8" can be expected.

Voids: Fastener holes and open knots can be present and may reach 1/2" in diameter in engineered and solid flooring or 1" diameter in solid paneling. Larger voids are occasionally included to preserve long lengths. Surface defects from insect marks, including pin holes may be present.

Discoloration: Ferrous staining from previous fasteners may be present.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse

(materials used for this credit cannot be applied to MRc4 or MRc5)

MRc4: Recycled Content, 100% Post-Consumer Recycled Content

(materials used for this credit cannot be applied to MRc3 or MRc7)

MRc5: Regional Materials (call for details)

MRc7: Solid Materials are FSC Recycled 100%; Engineered FSC Mix

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change.
All photos for representation only. Additional information available at our website or call our wood design experts.