

# American Prairie—Corral Board



**Pioneer Millworks**  
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Our American Prairie Corral Board is sourced from, you guessed it, working animal corrals. What makes this product unique is its thickness and length, allowing for greater spans and more material. We're fond of the occasional shadow marks that happen on boards not exposed fully to the elements, which gives this grade a geometric flair with stripes of browns on grey. A bit more consistent than our other American Prairie options, this barn wood siding comes in your choice of 5" or 7" single widths.



# Pioneer Millworks American Prairie—Corral Board

6/20/19

## CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

06 42 00—Wood Paneling  
07 46 23—Wood Siding

## MANUFACTURER

Pioneer Millworks  
1180 Commercial Drive  
Farmington, NY 14425  
Phone: 800-951-9663

Pioneer Millworks  
2609 SE 6th Avenue  
Portland, OR 97202  
Phone: 503-719-4800

## MATERIALS

1. **Product Name:** American Prairie Corral Board
2. **Species/Description:** American Prairie Corral Board
3. **Source:** Agricultural deconstruction
4. **Color:** Tones may range from dark to silver grey. Unlimited color variation is inherent to the product.
5. **Grade:** Corral Board
6. **Dimensions:**
  - Solid**  
TH— 5/8" to 1" variable  
WD— 5" or 7" as specified  
LG— 24" to 16' random
  - Engineered**  
TH—N.A.  
WD—N.A.  
LG—N.A.
7. **Milling:** Ripped on two edges, sawn on one face (R2ER1S)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 420–620  
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
  - Solid:** FSC Recycled 100%
  - Engineered:** N.A.

## ADDITIONAL INFORMATION

**Heartwood:** No restriction.

**Grain:** No restriction.

**Knots:** No limitations on sound knots, surface defects from chipped or open knots may be present.

**Texture:** This mixture shows a varied pattern of saw marks, wear patterns, colors and textures. Overwood of up to 1/4" can be expected.

**Voids:** Fastener holes and open knots can be present and occasionally reach 2" in diameter. Surface defects from insect marks, including pin holes may be present.

**Discoloration:** Ferrous staining from previous fasteners may be present as well as occasional shadow marks where the surface wasn't exposed to weathering.

**Checks:** Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

**Moisture Content:** Kiln dried 6–9% prior to milling.

## LEED INFORMATION

**MRc3:** Materials Reuse (materials used for this credit cannot be applied to MRc4 or MRc5)

**MRc4:** Recycled Content, 100% Post-Consumer Recycled Content (materials used for this credit cannot be applied to MRc3 or MRc7)

**MRc5:** Regional Materials (call for details)

**MRc7:** Solid Materials are FSC Recycled 100%

## RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.