

Modern Farmhouse Casual White Oak

Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Our Modern Farmhouse Casual White Oak makes the most of live sawn boards, preserving sound knots and embracing color variation. Made with FSC® Mix Certified lumber, this grade maximizes the yield of each log and is true to the organic nature of the tree in terms of appearance. Colors range from tan to brown.



Pioneer Millworks

Modern Farmhouse Casual White Oak

1/2021

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Modern Farmhouse Casual White Oak
2. **Species/Description:** Domestic White Oak, smooth planed
3. **Source:** Sustainably Harvested Forests
4. **Color:** Tones may range from cream to brown. Unlimited color variation is inherent to the product.
5. **Grade:** Casual
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—3" to 9" as specified
LG—18" to 144" random
 - Engineered**
TH—5/8"
WD—4" to 9" as specified
LG—12" to 90" random
7. **Milling:**
 - Unfinished: Tongue and Groove Square Edge (TGSQE),
 - Prefinished: Tongue and Groove Micro Bevel Edge (TGMBVE)
8. **Finish:** Unfinished unless specified otherwise.
9. **Hardness:** 1260
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)

ADDITIONAL INFORMATION

Heartwood: No limitation on heartwood.

Grain: No limitation on grain orientation.

Knots: No limitation on sound knots.

Texture: Surface should be 100% clear of saw marks.

Voids: Chipped or open knots can be present and occasionally reach up to 1/2" diameter so long as the voids do not extend to the edge of the board. Larger voids may occasionally be included to preserve long lengths.

Discoloration: Unlimited mineral staining is permitted.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRC3: N.A.

MRC4: N.A.

MRC5: Regional Materials (call for details)

MRC7: Certified Wood—Materials are FSC Mix

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.