

# Premium Select Vertical Grain—Heart Pine



Coming straight from the heart of Longleaf Southern Yellow Pine timbers used in industrial construction, this reclaimed wood is a classic. Its high resin content means it's hard and durable (like a hardwood) and gives Heart Pine its characteristic deep amber grain. The Vertical Grain variation is the most formal, with limited knots and nail holes, and a dense, linear grain pattern.



# Pioneer Millworks

## Premium Select Vertical Grain—Heart Pine

5/2022

### CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood strip and plank flooring  
06 42 00—Wood Paneling

### MANUFACTURER

Pioneer Millworks East  
1180 Commercial Drive  
Farmington, NY 14425  
Phone: 800-951-9663

Pioneer Millworks West  
2655 NE Orchard Ave.  
McMinnville, OR 97128  
Phone: 503-437-9017

### MATERIALS

1. **Product Name:** Premium Select Vertical Grain Heart Pine
2. **Species/Description:** Domestic Heart Pine, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range widely from amber to salmon. Unlimited color variation is inherent to the product.
5. **Grade:** Premium Select Vertical Grain
6. **Dimensions:**
  - Solid**  
TH—3/4"  
WD—3" to 5" random  
LG—18" to 12' random
  - Engineered**  
TH—N/A  
WD—N/A  
LG—N/A
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 1200  
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
  - Solid:** FSC Recycled 100%
  - Engineered:** FSC Mix

### ADDITIONAL INFORMATION

**Heartwood:** 85% or greater heartwood content.  
**Grain:** 90% or greater dense grain (8 rings or more per inch). 90% of grain should be vertical (60-90 degrees).  
**Knots:** Overall appearance should be 90% clear of knots. An average of one knot per 6 linear foot is permissible. Knots should not exceed 3/4" in diameter  
**Texture:** Surface should be 100% clear of saw marks or patina.  
**Voids:** Occasional nail holes up to 3/16" in diameter may be present.  
**Discoloration:** Minimal ferrous staining from previous fasteners may be present.  
**Checks:** No checking permitted.  
**Moisture Content:** Kiln dried 6–9% prior to milling.

### LEED INFORMATION

**MRC3:** Materials Reuse  
(materials used for this credit cannot be applied to MRC4 or MRC5)  
**MRC4:** Recycled Content, 100% Post-Consumer Recycled Content  
(materials used for this credit cannot be applied to MRC3 or MRC7)  
**MRC5:** Regional Materials (call for details)  
**MRC7:** Solid Materials are FSC Recycled 100%; Engineered FSC Mix

### RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.