

# American Prairie—Taphouse



*Pioneer Millworks*  
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Our take on barn wood paneling is broad and dynamic in scope. We incorporate wood that is salvaged not just from barns, but also from agricultural fencing and other structures that have endured the elements. Our Taphouse grade incorporates both external boards that have weathered grey patina and interior boards that have retained a brown patina. Good for use in both interior and exterior applications.



# Pioneer Millworks American Prairie—Taphouse

3/2023

## CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

06 42 00—Wood Paneling  
07 46 23—Wood Siding

## MANUFACTURER

Pioneer Millworks East  
1180 Commercial Drive  
Farmington, NY 14425  
Phone: 800-951-9663

Pioneer Millworks West  
2655 NE Orchard Ave.  
McMinnville, OR 97128  
Phone: 503-437-9017

## MATERIALS

1. **Product Name:** American Prairie Taphouse
2. **Species/Description:** Domestic Mixed Hardwoods and/or Softwoods with original patina
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from brown to grey.  
Unlimited color variation is inherent to the product.
5. **Grade:** Taphouse
6. **Dimensions:**  
**Solid**  
TH—5/8" to 1" variable  
WD—4" to 8" random, wider widths may be available upon request  
LG—2' to 12' random  
**Engineered**  
TH—N.A.  
WD—N.A.  
LG—N.A.
7. **Milling:** Ripped on two edges (R2E), surfaced 3 sides (S3S) available upon request
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 420–1100  
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)  
**Solid:** FSC Recycled 100%  
**Engineered:** N.A.

## ADDITIONAL INFORMATION

**Heartwood:** No restriction

**Grain:** No restriction

**Knots:** No limitations on sound knots, surface defects from chipped or open knots may be present.

**Texture:** This mixture shows a varied pattern of saw marks, wear patterns, colors and textures. Overwood of up to 1/4" can be expected.

**Voids:** Fastener holes and open knots can be present and occasionally reach 2" in diameter. Surface defects from insect marks, including pin holes may be present.

**Discoloration:** Ferrous staining from previous fasteners may be present.

**Checks:** Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

**Moisture Content:** Kiln dried 6–9% prior to milling

## LEED INFORMATION

**MRC3:** Materials Reuse

(materials used for this credit cannot be applied to MRC4 or MRC5)

**MRC4:** Recycled Content, 100% Post-Consumer Recycled Content

(materials used for this credit cannot be applied to MRC3 or MRC7)

**MRC5:** Regional Materials (call for details)

**MRC7:** Solid Materials are FSC Recycled 100%

## RECOMMENDED OVERAGE

Recommend 10-15% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.