



## Clear Vat Stock

### Vinegar Vat Stock Patina & Center Cut: Batch #15091

Salvaged from vinegar vats, this material is primarily made up of Cypress and Douglas fir and is smooth planed, exposing the tight clear grain and the blondish-amber color tones of the wood. Typically, 10–20% of these planks will include some dark staining.

### CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 20 — Reclaimed Wood Flooring

06 42 00 — Wood Paneling

### MANUFACTURER

Pioneer Millworks  
1180 Commercial Dr  
Farmington, NY 14425

### MATERIALS

Product: Clear Vat Stock

Collection: Reclaimed

Species: Primarily Cypress and Douglas Fir

Texture: Smooth Planed

Source: Salvaged Vat Stock

Color: Tones may range from deep brown to charcoal.

*May include occasional paint, old machine oil stains, and a range of wear marks.*

Finish: Unfinished

Hardness: 660

*(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)*

### DIMENSIONS & MILLING

**Solid** ( Unfinished )

Thickness: 5/8"

Profile

**TGMBVE**  
(Tongue and Groove Micro-Bevel Edge)

Width: 3"– 8" nominal

Length: 18"– 12' random

### ADDITIONAL INFORMATION

**Heartwood:** No Restriction

**Grain:** No Restriction

**Knots:** Primarily free of knots.

*Existing knots generally do not exceed 1/2" in diameter.*

**Discoloration:** Typically, 10–20% of these planks will include some dark staining.

**Checks:** Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

**Moisture Content:** Kiln dried 6–9% prior to milling.

### CERTIFICATIONS & LEED INFORMATION

**FSC® Claim:** FSC® Recycled 100% (SCS-COC-003998-D)

**MRC3:** Materials Reuse

*(materials used for this credit cannot be applied to MRC4 or MRC5)*

**MRC4:** Recycled Content, 100% Post-Consumer Recycled Content

*(materials used for this credit cannot be applied to MRC3 or MRC7)*

**MRC5:** Regional Materials (call for details)

### INSTALLATION RECOMMENDATIONS


**Overage:** Minimum 10% additional material

*for on-site grading, trimming and installation factors.*

**Climate:** As with any wood flooring or paneling product, the room temperature should be held at a consistent range between **60-80° F** with relative humidity between **30-60%**.

*Environmental conditions consistently outside of these parameters could result in product performance issues.*

**Solid** ( Unfinished )



**TGMBVE**  
Non-End Match

