


# Larch Siding & Shiplap

Pioneer Millworks Larch Siding and Shiplap is PEFC sourced Larch.

The signature swirling grain and small tight knots of larch brings a natural finish to vertical applications. The rot resistance of this underutilized species rivals that of Douglas fir, and it is locally grown in the Pacific Northwest which makes it a great option for exterior or interior uses. Pair it with one of our color options which show off the wood grain patterns through hue and tone; it has been brushed which enhances color saturation & adhesion.



# CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

**06 42 00** — Wood Paneling

07 46 23 - Wood Siding

#### **MANUFACTURER**

Pioneer Millworks 2655 NE Orchard Ave McMinnville, OR 97128

### **MATERIALS**

Product: Larch Shiplap

Collection: Siding & Shiplap

Species: Western Larch (Larix occidentalis)

Texture: Wire-Brushed

Source: Sustainably Harvested Forests

Color: Available prefinished, standard and custom colors available. Unfinished wood tone ranges from cream to light brown; color variation is inherent to the product.

Grade: Sound Tight Knots (STK)

Finish: Prefinished with a exterior sealer as specified (2 coats face, one coat back) \* shown Unfinished

Hardness: 830

(Janka Ball Test ASTM D143, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)

## **DIMENSIONS & MILLING**

Solid (Prefinished)

Thickness: 5/8" SHIPLAP (No Reveal)

SHIPLAP (With Reveal)

SHIPLAP (With Reveal)

Width: 5" face SQUARE-EDGE (S4S)

Length: 8'-16' random (Tongue and Groove Called lengths available Bevel Edge)

**TGBVE** 

#### **ADDITIONAL INFORMATION**

Heartwood: No Restriction

Grain: No Restriction

Knots: No limitations on sound knots.

surface defects from chipped or open knots may be present.

Voids: Occasional blown out knots up to 1" diameter may be present.

Checks: Checks allowed so long as material integrity is not adversely affected.

Moisture Content: Kiln dried 12–15% prior to milling.

### **CERTIFICATIONS & LEED INFORMATION**

MRc5: Regional Materials (call for details)

PEFC Certified Larch

### INSTALLATION RECOMMENDATIONS

Overage: Minimum 10% additional material

for on-site grading, trimming and installation factors.

Climate: As with any wood product, extreme climate conditions including heat, cold, humid or arid can cause movement and performance issues with the material.

