


Larch Shiplap



Pioneer Millworks | Larch Shiplap

Pioneer Millworks Larch Siding and Shiplap is PEFC sourced Larch. The signature swirling grain and small tight knots of larch brings a natural finish to vertical applications. The rot resistance of this underutilized species rivals that of Douglas fir, and it is locally grown in the Pacific Northwest which makes it a great option for exterior or interior uses. Pair it with one of our color options which show off the wood grain patterns through hue and tone; it has been brushed which enhances color saturation & adhesion.

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

06 42 00—Wood Paneling 07 46 23—Wood Siding

MANUFACTURER

Pioneer Millworks East 1180 Commercial Drive Farmington, NY 14425 Phone: 800-951-9663 Pioneer Millworks West 2655 NE Orchard Ave. McMinnville, OR 97128 Phone: 503-437-9017

MATERIALS

Product Name: Larch Siding & Shiplap

Species/Description: Western Larch (Larix occidentalis). Brushed for superior finish adhesion and color longevity

Source: PEFC-Certified Sources

Color: Available prefinished, standard and custom colors available.

Unfinished wood tone ranges from cream to light brown; color variation is inherent to the product.

Grade: Sound Tight Knots (STK).

Dimensions:

Solid—Shiplap

TH—5/8" WD—5" face

LG—8' to 16' random, called lengths available.

Milling: Shiplap no reveal, shiplap "nickel-gap", square-edge (S4S),

or TGBVE.

Finish: Prefinished with a exterior sealer as specified

(2 coats face, one coat back).

Hardness: 830

(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled).

FSC Claim: None.

ADDITIONAL INFORMATION

Heartwood: No restriction. **Grain:** No restriction.

Knots: No limitations on sound knots, surface defects from

chipped or open knots may be present.

Texture: Brushed.

Voids: Occasional blown out knots up to 1" diameter may be present.

Checks: Checks allowed so long as material integrity is not adversely affected.

Moisture Content: Kiln dried 12–15% prior to milling.

LEED INFORMATION

MRc3: N/A MRc4: N/A

MRc5: Regional Materials (call for details).

MRc7: N/A

RECOMMENDED OVERAGE

Recommend 10-15% additional material for on-site grading, trimming and installation factors.



Larch Sand













Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.