


American Gothic Chestnut

Nearly driven to extinction by a fungal blight in the early 20th century, Chestnut is one of the few woods that are only available as reclaimed lumber. Our Chestnut is sourced from barns and reveals glowing golds and rich browns when fully milled.



CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 20 — Reclaimed Wood Flooring

09 64 30 — Engineered Wood Flooring

06 42 00 — Wood Paneling

MANUFACTURER

Pioneer Millworks 1180 Commercial Dr Farmington, NY 14425

MATERIALS

Product: American Gothic Chestnut

Collection: Reclaimed

Species: Reclaimed Chestnut

Core: 9-Ply FSC® Certified & TCSA Compliant Birch Plywood

Texture: Smooth Planed

Source: Agricultural Deconstruction

Color: Tones may range from gold to brown.

Unlimited color variation is inherent to the product.

Finish: Available in Naked and Pure

Hardness: 540

(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)

DIMENSIONS & MILLING

Engineered (Prefinished)

Thickness: 5/8"

Profile
+ End Match: (Tongue and Groove
Micro-Bevel Edge)

4"-6" random

4" – 6" random

wider widths may be Wear Layer: 3/16"

available upon request

Length: 18" – 12' Core: 1/2"

Solid (Unfinished)

Width:

Thickness: 5/8"

Profile
Profile
(Tongue and Groove Square Edge)

Profile
Square Edge)

3"- 5" random

Width: wider widths may be Back-Relief: Included

available upon request

Length: 18"- 12'

ADDITIONAL INFORMATION

Heartwood: No Restriction

Grain: No Restriction

Knots: No limitations on sound knots.

Surface defects from chipped or open knots may be present.

Texture: Surface should generally be 95% clear of saw marks or patina.

Voids: In prefinished product, voids up to 1" in diameter

will be filled with a black composite.

Insect marks, including pinholes, may also be present on the surface.

Discoloration: Ferrous staining from previous

fasteners may be present.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

Moisture Content: Kiln dried 6-9% prior to milling.

CERTIFICATIONS & LEED INFORMATION

FSC® Claim: GFA-COC-008489

Engineered Solid

FSC Mix Credit FSC Recycled 100%

MRc4: Building Product Selection and Procurement

(FSC Mix Credit / FSC Recycled 100%)

INSTALLATION RECOMMENDATIONS

Overage: Minimum 10% additional material

for on-site grading, trimming and installation factors.

Climate: As with any wood flooring product, the room temperature should be held at a consistent range between 60-80° F with relative humidity between 30-60%.

Environmental conditions consistently outside of these parameters could result in product performance issues.







Unfinished SKU# 13111310010

Naked SKU# 13111310111

Pure SKU# 13111310211