

Beech—American Gothic

Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Reclaimed from antique barn timbers, Beech features a light and warm blonde color that sometimes tends towards blush, and can be heavy on the insect marks—there is no mistaking this for a mass-produced plank. Hard and durable, Beech is a great choice for busy floors. Due to the agarian sourcing and likeness of species this reclaimed wood may contain a small percentage of Maple and Sycamore.



Pioneer Millworks

Beech—American Gothic

7/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** American Gothic Beech
2. **Species/Description:** Domestic Beech, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range from blonde to pink.
Unlimited color variation is inherent to the product.
5. **Grade:** American Gothic
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—3" to 8" as specified
LG—18" to 144" random
 - Engineered**
TH—5/8"
WD—4" to 8" as specified
LG—12" to 96" random
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 1300
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid:** Recycled 100%
 - Engineered:** FSC Mix 70%

ADDITIONAL INFORMATION

Heartwood: No restriction
Grain: No restriction
Knots: No limitations on sound knots, surface defects from chipped or open knots may be present.
Texture: Surface should generally be 95% clear of saw marks or patina.
Voids: Nail, bolt and other mechanical holes can be present and occasionally reach 3/8" in diameter. Surface defects from insect marks, including pin holes may be present. Peg or bolt holes are often left open in longer planks.
Discoloration: Ferrous staining from previous fasteners may be present.
Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.
Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse (materials used for this credit cannot be applied to MRc4 or MRc5)
MRc4: Recycled Content, 100% Post-Consumer Recycled Content (materials used for this credit cannot be applied to MRc3 or MRc7)
MRc5: Regional Materials (call for details)
MRc7: Solid Materials are FSC Recycled 100%; Engineered FSC Mix 70%

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.