

Douglas fir—Saw-kissed

Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Though we tend to champion the beauty of authentic patina and as-found surfaces, we have found that there are occasions where some added texture can make a reclaimed material even more visually compelling. With our saw-kissed Douglas fir we have artfully machined a circle sawn texture onto smooth boards that were salvaged from Pacific Northwest granary structures. The applied texture adds a gentle unifying rhythm to the wood which makes for a casual and warm paneling/ flooring product.



Pioneer Millworks

Douglas fir—Saw-kissed

7/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood Strip and Plank Flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Saw-kissed Douglas fir
2. **Species/Description:** Domestic Douglas fir with original patina
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range widely from tan to brown. Unlimited color variation is inherent to the product.
5. **Grade:** Saw-kissed
6. **Dimensions:**
 - Solid**
TH— 3/4"
WD— 5" nominal
LG— 18" to 144" random
 - Engineered**
TH—N.A.
WD—N.A.
LG—N.A.
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Includes a Pure hardwax oil finish (flooring) or a single coat interior oil (paneling).
9. **Hardness:** 620
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid:** Recycled 100
 - Engineered:** N.A.

ADDITIONAL INFORMATION

Heartwood: No restriction.

Grain: No restriction.

Knots: No limitations on sound knots, surface defects from chipped or open knots may be present. Knots typically do not exceed 3" in diameter.

Texture: Material to have original patina with applied circle saw marks. Overwood of up to 1/8" can be expected.

Voids: Unlimited nail holes and occasional bolt holes are permissible.

Discoloration: Ferrous staining from previous fasteners may be present.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.

Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRC3: Materials Reuse (materials used for this credit cannot be applied to MRC4 or MRC5)

MRC4: Recycled Content, 100% Post-Consumer Recycled Content (materials used for this credit cannot be applied to MRC3 or MRC7)

MRC5: Regional Materials (call for details)

MRC7: Solid Materials are FSC Recycled 100%

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



The mark of responsible forestry



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.