Sustainably Harvested—Walnut



Sourced from carefully managed forests, this high-grade, this high-grade Walnut offers a more uniform appearance than its reclaimed counterpart. Expect consistent color tones ranging from brown to purple and a few small knots. This sustainably harvested wood pairs especially well with our custom eco-friendly finishes for floors and paneling.



Pioneer Millworks Sustainably Harvested—Walnut

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29-Wood strip and plank flooring 06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks 1180 Commercial Drive Farmington, NY 14425 Phone: 800-951-9663

Pioneer Millworks 2609 SE 6th Avenue Portland, OR 97202 Phone: 503-719-4800

MATERIALS

- 1. Product Name: Sustainably Harvested Walnut
- 2. Species/Description: Domestic Walnut, smooth planed
- 3. Source: Sustainably Harvested Forests
- 4. **Color:** Tones may range from brown to purple. Unlimited color variation is inherent to the product.
- 5. Grade: Select and Better
- 6. Dimensions:

Solid

TH-N.A. WD-N.A.

LG-N.A.

Engineered

TH-1/2" or 5/8" as specified WD-4" to 8" as specified LG—12" to 96" random

- 7. Milling: Tongue and Groove Square Edge (TGSQE)
- 8. Finish: Unfinished unless specified otherwise
- 9. Hardness: 1320

(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)

10. FSC Claim: None

ADDITIONAL INFORMATION

Heartwood: 75% or greater Heartwood

Grain: Clear

Knots: Primarily free of knots. Existing knots generally do not exceed 1/4" diameter.

Texture: Surface is fully planed and clear of saw marks.

Voids: No voids are permitted.

Discoloration: Limited mineral staining is permitted.

Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the

material increases.

Substrate: FSC Baltic Birch CPCP grade 9mm thickness for finished 1/2" 12mm thickness for finished 5/8"

No Urea Formaldehyde added (Note: wood has trace amounts naturally)

Glue: Formaldehyde-free low VOC glue

Moisture Content: Kiln dried 6-9% prior to milling.

LEED INFORMATION

MRc5: Regional Materials (call for details)

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.

















Information is deemed reliable but subject to change, All photos for representation only. Additional information available at our website or call our wood design experts.