

White Pine—Knotty'N'Naily



Pioneer millworks
RECLAIMED & SUSTAINABLE WOOD PRODUCTS



Eastern White Pine has been used in construction and furniture making for centuries, and this reclaimed grade gives you the classic knotty pine look. Starting creamy white

when milled and deepening to a warm amber over time, it's sometimes called pumpkin pine, and it's softwood nature means it will continue to wear and patina after installation for an authentic, historic look.



Pioneer Millworks

White Pine—Knotty 'N' Naily

7/2018

CUT AND PASTE SPECIFICATION INTO APPROPRIATE CSI DIVISION

09 64 29—Wood strip and plank flooring
06 42 00—Wood Paneling

MANUFACTURER

Pioneer Millworks
1180 Commercial Drive
Farmington, NY 14425
Phone: 800-951-9663

Pioneer Millworks
2609 SE 6th Avenue
Portland, OR 97202
Phone: 503-719-4800

MATERIALS

1. **Product Name:** Knotty 'N' Naily White Pine
2. **Species/Description:** Domestic White Pine, smooth planed
3. **Source:** Agricultural/Industrial deconstruction
4. **Color:** Tones may range widely from cream to pink.
Unlimited color variation is inherent to the product.
5. **Grade:** Knotty 'N' Naily
6. **Dimensions:**
 - Solid**
TH—3/4"
WD—3" to 10" as specified
LG—18" to 144" random
 - Engineered**
TH—N.A.
WD—N.A.
LG—N.A.
7. **Milling:** Tongue and Groove Square Edge (TGSQE)
8. **Finish:** Unfinished unless specified otherwise
9. **Hardness:** 380
(Janka Ball Test ASTM D1037-96A, Natural wood products have no minimum hardness since hardness is a characteristic of species and cannot be controlled)
10. **FSC Claim:** (SCS-COC-003998)
 - Solid:** Recycled 100%
 - Engineered:** N.A.

ADDITIONAL INFORMATION

Heartwood: No restriction
Grain: No restriction
Knots: No limitations on sound knots, surface defects from chipped or open knots may be present. Knots typically do not exceed 3" in diameter.
Texture: Surface should generally be 95% clear of saw marks or patina.
Voids: Unlimited nail holes and occasional bolt holes are permissible.
Discoloration: Ferrous staining from previous fasteners may be present.
Checks: Structural checks not affecting the integrity of the plank, once installed, are allowed and more prevalent as the width of the material increases.
Moisture Content: Kiln dried 6–9% prior to milling.

LEED INFORMATION

MRc3: Materials Reuse
(materials used for this credit cannot be applied to MRc4 or MRc5)
MRc4: Recycled Content, 100% Post-Consumer Recycled Content
(materials used for this credit cannot be applied to MRc3 or MRc7)
MRc5: Regional Materials (call for details)
MRc7: Solid Materials are FSC Recycled 100%

RECOMMENDED OVERAGE

Recommend 7–12% additional material for on-site grading, trimming and installation factors.



Information is deemed reliable but subject to change. All photos for representation only. Additional information available at our website or call our wood design experts.